

CERTIFICATE OF ANALYSIS

Client Code:	Wiper Supply	Flushable		Date: 07.26, 2019		
Model	CR3050		Lot No	190726104		
Test Items		Test Result	Standard values	Test Standards	Pass/Fail	
GSM	(g/m ²) AVG	51.2	46.5-53.5	FZ/T64012-2013	Pass	
	CV(%)	/	≤7		Pass	
Thickness (mm)		0.54	0.50-0.56	FZ/T64012-2013	Pass	
Width (mm)		170	167-173	FZ/T64012-2013	Pass	
Liquid Absorption(%)		951	/	/	Pass	
(N/5cm) Breaking strength dry	MD	16.80	≥15	FZ/T64012-2013	Pass	
	CD	7.80	≥7		Pass	
(%) Breaking elongation dry	MD	7.10	≤30		Pass	
	CD	35.10	≤50		Pass	
(N/5cm) Breaking strength wet	MD	5.40	≥5		Pass	
	CD	3.30	≥3		Pass	
(%) Breaking elongation wet	MD	23.90	≤40		Pass	
	CD	55.00	≤70		Pass	
Slosh Box Disintegration Test	(min) * Sloshing Time	10	5-180		INDA/EDANA GD4 Flushability Testing	Pass
	(%) Pass Rate	97.8	70-100			Pass
pH		/	5.5-8.5	FZ/T64012-2013		
(CFU/g) Microbe		/	<200	FZ/T64012-2013		
Surface Appearance		Pass		FZ/T64012-2013		
Evaluation	Pass					