



Company: Wiper Supply Services Limited

Item Name / No.: 35gsm Wavy Line Woodpulp/Spunlace

Data Table Overview

Parameter / Test Item PDF	Specification / Target PDF	Test Result	Standard / Reference PDF
Composition (%)	Wood pulp: 50 ± 2% Polyester: 50 ± 2%	Wood pulp: 50% Polyester: 50%	Corporation Standards
Basis Weight (g/m^2 , gsm)	35 ± 5%	34.2	GB/T 24218.1-2009
Thickness (mm)	—	0.23	GB/T 24218.2-2009
Capacity of Liquid Absorbability (%)	—	575	GB/T 24218.6-2010
Whiteness Degree (%)	—	—	GB/T 3978-2008
Breaking Strength - CD (N/5cm)	—	8.93	GB/T 24218.3-2010
Breaking Strength - MD (N/5cm)	—	53.81	GB/T 24218.3-2010
Breaking Elongation - CD (%)	—	143.09	GB/T 24218.3-2010
Breaking Elongation - MD (%)	—	15.54	GB/T 24218.3-2010

Additional Information:

- **Date of Test:** July 4, 2026 (2026.7.4)
- **Tester:** Ren Xuhua (任绪华)
- **Approval / Test Seal:** Approved

